

Partial Translation of
Japanese Unexamined Utility Model Publication (U) No. H03-70288

Claim: A vehicle sheet lining fabric which is a nonwoven fabric formed by three-dimensionally interlacing filaments, the fabric having a basis weight of 10 g/m^2 to 60 g/m^2 , a tensile stress in the machine direction of 0.2 kg/5 cm to 2.0 kg/5 cm at 5% elongation, a tensile stress in the transverse direction of not higher than 2.0 kg/5 cm at 5% elongation, a tensile strength of at least 2.0 kg/5 cm in both the machine and transverse directions, an elongation of at least 60% in both the machine and transverse directions, and a tear strength of at least 0.5 kg in both the machine and transverse directions.

Brief Description of the Drawing

Fig. 1 is a cross-sectional view of a vehicle sheet comprising the vehicle sheet lining fabric of the present model.

1. Outer material
2. Cushioning material
3. Lining fabric



Creation date: 09-12-2006
Indexing Officer: KTO - KIM THU TO
Team: ZZZFEP
Dossier: 10589503

Legal Date: 09-07-2006

| No. | Doccode | Number of pages |
|-----|---------|-----------------|
| 1 | IDS | 2 |
| 2 | FOR | 10 |
| 3 | FOR | 70 |

Total number of pages: 82

Remarks:

Order of re-scan issued on